

Horse HM-1.2T

Unidirectional Carbon Fiber Laminate For Strengthening

Description	HM-1.2T is a high strength, high modulus unidirectional carbon fiber reinforce polymer(CFRP) for structural strengthening. It is bonded onto the structure as external reinforcement using HM-120CP epoxy resin as the adhesive.
Application Range	Load Increase
	Increased live loads in warehouses
	Increased traffic volumes on bridges
	Installation of heavy machinery in industrial buildings
	Vibrating structures
	Changes of building utilization
	Seismic Reinforcement
	Concrete column wrapping, beam strengthening, wall
	strengthening, slab strengthening
	Masonry walls reinforcement
	Damage to Structural Parts
	Aging of construction materials
	Fire
	Vehicle impact
	Change of Structural System
	Removal of walls or columns
	Removal of slab sections for openings
	Design or Construction Defects
	Lack of reinforcing bars
	Lack of member cross section
	Improve Structural State
	Reduce the deformation
	Reduce the stress of the original structure
	The crack reinforcement



Product Characteristic	High strength, high toughness, high modulus
	Soft and flexible, light self weight, easy to install
	Long shelf life and aging resistance
	High temperature resistance
	Acid, alkali & salt resistance
	Seismic resistance
	Environmental-friendly
	Can be used for shear strengthening, confinement
	strengthening, flexural strengthening
Horse Advantage	Aviation Grade Yarn
	Japan imported aviation grade raw material, excellent
	quality and stable performance.
	World Leading Production Line
	Germany imported intelligent production line. Point to
	point active weft insertion. No damage to the yarn during
	the weaving process.
	excellent flatness enable epoxy easy to penetrate, hence
	high bonding strength can be achieved
	Patented Tension Controling System
	Our own developed whole process tension controling
	system. It ensures the constant tension, low dispersion.
	Large output and Timely Delivery
	5 million square meters annual output. 100 thousand
	square meters regular daily stock.
Package	This product is rolled into a ring and uses a belt to bind.
	Each roll is 100 meters length.
	When the laminate width is 50mm, two rolls will be put
	into one carbon box;
	When the width is 100mm, one roll in one carbon box;



Basic Information

Model	HM-1.2T
Appreance	Black laminate
Length	100m
Width	Regular width is 50mm, 100mm, other width can be customized.
Shelf Life	50 years
Storage Conditions	Store in dry conditions at 4°C to 35°C
Braiding	0° (Unidirectional)

Performance Indexes

The results are tested by Syracuse University USA according to ASTM standards. Original test reports available.

For more about ASTM (American Society for Testing Materials), please refer to https://www.astm.org

Tensile Strength (ASTM D3039)	2743 Mpa
Tensile Modulus (ASTM D3039)	171 Gpa
Elongation at Break (ASTM D3039)	0.015
Flexural Strength (ASTM D7264)	2164 Mpa
Thickness	1.2mm
Temperature Resistance	>150°C
Fiber Content	≥65%
Density	1.6g/cm³



Construction Process

1. Setting out according to design;

2. Remove painting of the concrete surface and polish, blow out the floating dust with compressed air;

3. Prepare adhesive: Mix component A and B evenly in bucket. Mix ratio by weight A: B = 2:1 ;

4. Installing: Paste the epoxy onto the surface of carbon fiber plate evenly, please avoid bubbles;

5. Anchorage: Paste the carbon fiber plate onto the concrete surface and fixed with steel strip, remove extra epoxy near the plate, and fix with steel framework;

6. Maintenance: Waiting for the epoxy to cure, curing time should be no less than 24 hours at room temperature.

Points for Attention	The construction workers should take necessary
	protective measures such as wearing masks, gloves,
	goggles etc. Pay attention to fire prevention and maintain
	good ventilation on site.
	Carbon fiber material is conductive, be careful to the
	electrical equipments around.

For more information, please visit our website at https://www.horseen.com

